




## ELEKTRIKGIPS

### Description

**Elektrikergips** is an excellent fit for quick fixing of electric tubes, electric doses, and other assembly parts. Pofiks Electrician gypsum is poured out in clean water.

Ready-mixed material can be processed in about 8 minutes.



### Preparation and Parameters application

Time for application after mixing with water	7 min.
Drying time of material	24 h.
Application thickness	3 - 5 mm.
Granulation	0-0.7 mm.
Consumption	4- 5 kg/m <sup>2</sup> .

**Preparation  
and Parameters  
application**

The  
temperature  
of the air  
and surface

+5/+35Â°C

Color

Kg bag 2.5

Bags/pallet 300

**Date Created**

01.05.2023

**Author**

admin

POFIX