



POBETONCONTACT STANDARD

Description

Pobetoncontact Standard

It is laid on internal and external smooth concrete surfaces. Pobetoncontact is ready for use. Before applying it is strongly recommended to mix the product well and add 10% clean water. It is laid manually using a cylindrical roller. The drying time is 24 hours.



POFIX

Preparation and application

Time for application after mixing with water

Parameters

2 h.

Drying time of material

12 h.

Application thickness

1-2 mm.

Granulation

0-1.2 mm.

Consumption

350 g/m².

The temperature of the air and surface

+5/+25°C

Color

Kg bag

10/20

Bags/pallet

60/36

Date Created

06.05.2023

Author

admin