



POBETONCONTACT

Description

Pobetoncontact

It is laid on internal and external smooth concrete surfaces. Pobetoncontact is ready for use. Before applying it is strongly recommended to mix the product well and add 10% clean water. It is laid manually using the cylindrical roller.

The drying time is 24 hours.



Preparation and application

Time for application after mixing with water

Drying time of material

Application thickness

Granulation

Consumption

The temperature of the air and surface

Color

Kg bag

Bags/pallet

Parameters

2 h.

12 h.

1 - 2 mm.

0-1.2 mm.

350 g/m².

+5/+25°C

10/20

60/36

Date Created

06.05.2023

Author

admin