




POFIX 200

Description

Glazing

Pofix 200 is powder material-glazing on the basis of plaster for internal walls used manually. It is used for leveling the walls in thin layers, for smoothing rough surfaces, and various corrections on the surfaces (ex. for filling cracks). It is laid after the basic mortar is completely dry (Pofix 10, Pofix 090, etc). After it is completely dry the walls can be colored or it could be put on paper walls, etc. Before applying Pofix 200, it is recommended to use Potiefgrund.



Preparation and application

Parameters

Time for application after mixing with water	60 min.
Drying time of material	24 h.
Application thickness	1.5 mm.

**Preparation
and Parameters
application**

Granulation 0 - 0.5 mm.

Consumption 1.5 kg/m².

The
temperature
of the air +5/+35°C
and surface

Color

Kg bag 20

Bags/pallet 60

Date Created

01.05.2023

Author

admin

POFIX