




POFIX 222

Description

Glazing

Pofix 222 is powder material-glazing on the basis of plaster for internal walls used manually. It is used for leveling of the walls in thin layers, smoothing rough surfaces, and various corrections on the surfaces (ex. for filling cracks). It is laid after the basic mortar is completely dry (Pofix 10, Pofix 090, etc). After it is completely dry the walls can be colored or it could be covered with paper walls, etc. Before applying Pofix 222, it is recommended to use Potiefgrund.



Preparation and application

Parameters

Time for application after mixing with water	60 min.
Drying time of material	24 h.
Application thickness	1.5 mm.

**Preparation
and Parameters
application**

Granulation 0 - 0.3 mm.

Consumption 1.5 kg/m².

The
temperature
of the air +5/+35Â°C
and surface

Color

Kg bag 20

Bags/pallet 60

Date Created

01.05.2023

Author

admin

POFIX