




POFIX 366

Description

White structural mortar - ABRIB

Pofix 366- Atrib is fabricated, enabling the decoration of mineral mortar for internal walls. It is laid over the basic mechanical mortars (Pofix 10, Pofix 090, etc.) thermo-isolation, lengthening mortars, eps, and mineral woolen boards which are previously flattened with Pofix 50. Before applying Pofix 366 it is recommended to use Poputzgrund.



Preparation and Parameters application

Time for
application
after mixing
with water

60 min.

Drying time
of material

24 h.

Application
thickness

1 mm; 1.5 mm; 2 mm

Granulation

3 mm.

Consumption 2 – 4 kg/m².

**Preparation
and Parameters
application**

The
temperature
of the air +5/+35Â°C
and surface

Color

Kg bag 25

Bags/pallet 48

Date Created

01.05.2023

Author

admin

POFIX