



## POFIX-50

### Description

#### Flattening Mortar

**Pofix 50** is a fabricated mortar for external and internal use. It is used as mortar for flattening and joint between the basis and structural mortar 'abrib'.

#### Preparation and application Parameters

Time for application after mixing with water	30 min.
Drying time of material	24 h.
Application thickness	1-1.5 mm.
Granulation	0.7 mm.
Consumption	1.5-2 kg/m <sup>2</sup> .

**Preparation  
and Parameters  
application**

The  
temperature  
of the air  
and surface

+5/+35Â°C

Color

Kg bag 25

Bags/pallet 48

**Date Created**

01.05.2023

**Author**

admin

POFIX