




## POFIX 701 FULL

### Description

#### White structural mortar - ABRIB

**Pofix 701 FULL**-Abrib is fabricated, enabling the decoration of mineral mortar for external walls. It is laid over the basic mechanical mortars (Pofix 10, Pofix 090, etc.) thermo-isolation, lengthening mortars, eps, and mineral woolen boards which are previously flattened with Pofix 50. Before applying Pofix 705 it is recommended to use Poputzgrund.



### Preparation and application

#### Parameters

Time for application after mixing with water	60 min.
Drying time of material	24 h.
Application thickness	1.5 – 2 mm.
Granulation	1.5 – 2 mm.

**Preparation  
and Parameters  
application**

Consumption 2 - 4 kg/m<sup>2</sup>.

The  
temperature  
of the air +5/+35Â°C  
and surface

Color

Kg bag 25

Bags/pallet 48

**Date Created**

01.05.2023

**Author**

admin

POFIX