




POFIX 705

Description

White structural mortar - ABRIB

Pofix 705-Abriss is fabricated, enabling the decoration of mineral mortar for external walls. It is laid over the basic mechanical mortars (Pofix 10, Pofix 090, etc.) thermo-isolation, lengthening mortars, eps, and mineral woolen boards which are previously flattened with Pofix 50. Before applying Pofix 705 it is recommended to use Poputzgrund.



Preparation and application Parameters

Time for application after mixing with water	60 min.
Drying time of material	24 h.
Application thickness	1 mm; 1.5 mm; 2 mm
Granulation	3 mm.
Consumption	2-4 kg/m ² .

**Preparation
and Parameters
application**

The
temperature
of the air
and surface

+5/+35Â°C

Color

Kg bag 25

Bags/pallet 68

Date Created

01.05.2023

Author

admin

POFIX