




POFIX-75 LIGHT

Description

Basic final mortar

Pofix 75-Light is a fabricated plaster mortar for mechanical treatment. It is used for covering internal walls in one layer. It can be spread brick walls, concrete blocks, concrete walls, siporex blocks, etc. The base surface must be dry, dust and oil must be removed and it must satisfy building standards.



Preparation

and Parameters application

Time for application after mixing with water	3-4 h.
Drying time of material	48 h.
Application thickness	1.7 mm.
Granulation	0.7 mm.
Consumption	15 kg/m ² .

**Preparation
and Parameters
application**

The
temperature
of the air
and surface

+5/+35Â°C

Color

Kg bag 30

Bags/pallet 42

Date Created

01.05.2023

Author

admin

POFIX