




## POFIX FINO

### Description

#### Basic cement mortar

**Pofix fino** is a cement lime mortar with additives for manual laying.

It is applied on two layers of internal and external walls after the basic mortar is applied.



### Preparation and Parameters application

Time for  
application  
after mixing  
with water 60 min.

Drying time  
of material 24 h.

Application  
thickness 2-3 mm.

Granulation 0.7 mm.

Consumption 2-3 kg/m<sup>2</sup>.

**Preparation  
and Parameters  
application**

The  
temperature  
of the air  
and surface

+5/+35Â°C

Color

Kg bag 25

Bags/pallet 48

**Date Created**

01.05.2023

**Author**

admin

POFIX