



## POPUTZGRUND

### Description

#### Poputzgrund

It is a basic resin for internal and external use. Before applying the product should be mixed with 30% clean water. It is laid manually with a brush or cylindrical roller. At dry and porous surfaces Poputzgrund should be applied twice between 2-3 hours. The drying time is 24 hours. Keep on places protected from freezing.



#### Preparation and application

Time for application after mixing with water

Drying time of material

Application thickness

Granulation

Consumption

The temperature of the air and surface

Color

Kg bag

Bags/pallet

#### Parameters

2 h.

12 h.

1 - 2 mm.

0-0.7 mm.

350 g/m<sup>2</sup>.

+5/+25°C

8/19

60/36

#### Date Created

06.05.2023

#### Author

admin